Threaded rods

Fully threaded rods. Metric coarse and fine pitch, left-hand and inch-thread executions according to specification.

Rods and tie rods



Representative photograph. The approved drawing defines the supplied geometry.

Execution: Fully threaded · Thread: Metric / inch

Technical drawing and legend



d	Nominal thread diameter. Also specify pitch or series and tolerance.
L	Overall end-to-end length.

Not to scale. Chamfers, transitions and thread runout according to the supply drawing.

Threads and dimensions

Reference diameter/pitch pairs, not an availability list. Fine-pitch and inch-thread executions are specified separately.

System	Designation	Required specification
Metric coarse	M	Nominal diameter and pitch P in mm
Metric fine	M × P	Pitch must be specified explicitly
UNC / UNF / 8UN	Inch	Diameter, series, threads per inch (TPI) and thread class
Whitworth	Inch	Specify the series; not automatically interchangeable with UNC/UNF

Metric coarse pitch: dimensional references

d	P (mm)
M4	0.7
M5	0.8
M6	1
M7	1
M8	1.25
M10	1.5
M12	1.75
M14	2
M16	2
M18	2.5
M20	2.5
M22	2.5
M24	3
M27	3
M30	3.5
M33	3.5
M36	4
M39	4
M42	4.5
M45	4.5
M48	5
M52	5
M56	5.5
M60	5.5

Materials and finishes

Material / specification	Grades and conditions
Carbon and alloy steels	Property classes 4.8 and 8.8; C40 executions documented by Piscetta. Other classes to specification.
A2 and A4 stainless steel	Specify execution and property class; documented by Piscetta, King and Tobsteel.
A5, A8 stainless; D6 duplex, D8 superduplex	Tobsteel DIN 976 reference: A8-80; D8-100; D6-80 (M27 and above: 70); A2/A4/A5-70 (M27 and above: 50). These classes do not automatically apply to other executions.
Brass	Threaded rods and fully threaded cut studs documented by Piscetta and Magnani; specify alloy.
Polyamide / nylon	Bossard BN 1072: natural PA 6.6, execution similar to DIN 975. Steel property classes do not apply.
ASTM A193	B7, B7M, B16; B8 and B8M class 1 or 2; B8A, B8MA, B8R, B8RA. Specify grade, class and project requirements.
ASTM A320	L7, L7M, L43; B8 and B8M class 1 or 2; B8A, B8MA. Requirements and testing according to specification.
ASTM A453 grade 660	Specify class and metallurgical condition in the enquiry.

Materials, ASTM grades and classes are separate alternatives, not combinations available for every diameter, pitch or process. For rolled tie rods, manufacturability and final properties require verification. Dueemme confirms execution and availability in the quotation.

Finishes

Plain/natural; for steels, electroplated zinc, hot-dip galvanizing, zinc-nickel, phosphating or PTFE/Xylan coatings according to specification. Select coating, thickness and thread tolerance compatible with material, class and service; not every finish applies to every variant.

Supply specification

Rod lengths

1000 / 2000 / 3000 mm, depending on material and execution. These three formats are not automatically available for every variant: polyamide BN 1072 is documented at 1000 mm. Confirm in the quotation.

Tolerances and inspection

Specify the thread standard, tolerance class, condition before/after coating and required inspection. Do not apply a single tolerance to metric threads, inch threads, polymers and rolled executions. Approved drawing dimensions and tolerances govern custom parts.

Oil & gas service and documentation

State the project specification, full grade and class, service temperature and environment, coating, marking and required documentation. Any NACE/ISO 15156, PED or inspection-certificate requirements must be explicitly agreed; an ASTM designation alone does not establish compliance.

Documentation

Document	Status
Declaration of conformity	Subject to order agreement
Material certificate	Subject to order agreement
EN 10204 2.2 test report	Subject to order agreement
EN 10204 3.1 inspection certificate	Subject to order agreement
Dimensional inspection report	Subject to order agreement
Coating report	Subject to order agreement
Other documentation	Subject to order agreement

Batch documents are not automatically included: specify your requirements in the RFQ.